

A

*Free of defects*



AB

*Where face may be visible, ideal for all types of finish (plating, clear varnish, satin finish etc.) Only a few pin knots or sound, tight ones without cracks are allowed. Slight discolorations, very small patches, or well-made repairs where color remains consistent with the rest of the surface are also allowed.*



B

*"Natural" face with color variations and sound knots, suitable for finishing with laminate covering, paint or varnish. May contain sound, tight knots no larger than 35 mm in diameter; small knot holes or hairline cracks, only if well-patched. Low-contrast discolorations, minor imperfections, glue marks, repairs and well-filled patches are also allowed.*



BB

*"Open" face, can be putty-filled upon request, suitable for uses where face is not visible. Sound, tight knots up to 50 mm in diameter are permissible; as are loose knots, cracks, bark pockets/inclusions and other irregularities. Discolorations, as long as they do not affect soundness, glue marks, repairs and patches of all kinds.*



C

*Plywood suitable for packaging or similar use where face grade is not critical. All natural wood features are allowed, along with various processing defects, as long as they do not compromise the functionality of the panel (for example: fungus growth and iron/mineral inclusions are not permissible).*

